



TECHNICAL DATA SHEET

SUPER LUBE® SYNTHETIC LIGHTWEIGHT OIL

January 2019

PRODUCT DESCRIPTION:

Super Lube® Synthetic Lightweight Oil has a lower viscosity than Super Lube® Oil with Syncolon® (PTFE). It should be used in place of conventional 8 – 10 cSt oils.

Super Lube® Lightweight Oil is ideal for misting, dripping, spindle oil applications and as a food-grade chain lubricant and rust inhibitor.

Super Lube® Lightweight Oil is an NSF registered Food Grade lubricant, rated H1 for incidental food contact. Meets former USDA (H1) guidelines.



FEATURES:

- ❖ Viscosity stable
- ❖ Long lasting
- ❖ Reduces friction and wear
- ❖ Waterproof
- ❖ Superior at low temperatures
- ❖ Prevents rust and corrosion
- ❖ Environmentally friendly
- ❖ Biodegradable
- ❖ Kosher certified
- ❖ NSF Registered H1, #136306
- ❖ Superior Heat Transfer

TYPICAL APPLICATIONS:

- ❖ General light oil applications
- ❖ Textile spindles
- ❖ Grinder arbor bearings
- ❖ Ring oiled bearings
- ❖ Wick feeds
- ❖ Airline oilers
- ❖ Oil cups
- ❖ Enclosed chains
- ❖ Light circulating systems
- ❖ Food grade chain lubricant
- ❖ Vacuum pump oil
- ❖ Spindle
- ❖ Circulating
- ❖ Hydraulic
- ❖ Food processing equipment

PACKAGE SIZES:

Part No.	Description
52004	4 oz. Bottle
52008	8 oz. Bottle
52020	1 Pint Bottle
52030	1 Quart Bottle
52040	1 Gallon Bottle
52050	5 Gallon Bottle
52150	15 Gallon Keg



TECHNICAL DATA SHEET

SUPER LUBE® SYNTHETIC LIGHTWEIGHT OIL

January 2019

52550

55 Gallon Drum

PROPERTIES:

Test	Test Method	Rating
Color:		Translucent
Temperature Range		
Continuous:		-40°F to 500°F (-40°C to 260°C)
Intermittent:		-40°F to 650°F (-40°C to 343°C)
Viscosity		
cSt @ 100°C:	ASTM D445	11
cSt @ 40°C:	ASTM D445	65
ISO Grade:		68
Replaces ISO Grades:		68-100
Replace SAE Grade Gear Oils		80W
Viscosity index	ASTM D227	161
Specific Gravity:	ASTM D1298	.89 @ 60°F
Pour Point:	ASTM D97	-40°F (-40°C) maximum
Water, PPM:	ASTM D1744	40 ppm
Tan:	ASTM D974	0.02 maximum
Four Ball Test	ASTM D2596 and D2783	
Load Wear Index:		27 kg
Weld Point:		130 kg
Four Ball EP Test Scar Diameter:	ASTM D2266 and D4172	< 0.5 mm
Salt Spray Test (100 hrs.):	ASTM B117	Pass
Dielectric Loss:	ASTM D924	1.2 x 10 ¹²
Dielectric Resistivity:	ASTM D1169	1.7 x 10 ¹²
Dielectric Constant:	ASTM D924	2.5
Evaporation Loss		
22 hrs. @ 212°F (100°C)	ASTM D972	< 2%
Oxidation Stability, 100 hrs.:	ASTM D942 and D943	4 psi
Flash Point:	ASTM D92	>450°F (232°C)
Fire Point:	ASTM D92	>525°F (300°C)
Copper Corrosion		
24 hrs. @ 100°C:	ASTM D4048 and D130	1A
Acid Number:	ASTM D664	0.5 mg KOH/g
Biodegradability:	CEC-L33-T82	50% degradability in 28-35 days 60+% degradability in 56 days



TECHNICAL DATA SHEET

SUPER LUBE® SYNTHETIC LIGHTWEIGHT OIL

January 2019

DIRECTIONS:

- Clean area to be treated.
- Apply oil.

SHELF LIFE / WARRANTY:

Super Lube® products have a five (5) year recommended shelf life when stored in the original container and in reasonable ambient conditions. The warranty period is twenty-four (24) months from the date of purchase. For complete information visit www.super-lube.com/what-is-the-shelf-life-ezp-320.html.



See Safety Data Sheet (SDS) for further details regarding safe use of this product.



Made in USA

The information provided in this Technical Data Sheet, including the recommendations for use and application of the product are based on our knowledge and experience of the product as of the date of this data sheet. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Synco Chemical Corporation is, therefore not liable for the suitability of our product for the production processes and conditions in respect for which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

All Super Lube® trademarks in this document are trademarks of Synco Chemical Corporation.

